

KATRET CH FLEX UV

Two-Component UV Resistant Extra Flexible Waterproofing Mortar

Product Description :

KATRET CH FLEX UV is cement-based, two-component, composed of white-colored cementitious compound and white-colored liquid emulsion, extra flexible and UV lights resistant sealing slurry that is reinforced by polymeric additives. It provides water insulation in roof, terraces and balconies. It is water-repellent and can be used from the positive side only.

Areas of application :

- From positive side only
- Both vertical and horizontal
- In wet volumes (WC, bathroom, kitchen etc.)
- In continuously wet, humid and damp areas such as balcony, terrace and cellar, water tanks, pools, reservoirs and storage tanks
- In foundations, basement walls, underground and surface construction works
- In bridges and sustaining walls

Features :

- Suitable for brush and spray use
- Extra flexible
- Resistant to UV lights
- Resistant to heavy weather conditions
- Provides impermeability against the pressured water effect
- High adherence; strongly adheres to surfaces
- High abrasion resistance
- Suitable for use without any coating on the drinking water tank

Technical data :

Colour	White
Applicable thickness (mm)	Max 6
Recommended applicable thickness (mm)	2
Dry unit volume weight (kg / lt)	1,2 ± 0,2
Wet unit volume weight (kg / lt)	1,7 ± 0,2
Waiting time in container (min)	~ 30
Drying time (hour)	~ 24
Carbondioxide permeability (m)	>50
Permeability to water-vapour (m)	Class I ; Sd <5
Adhesion strength (28 days) (N / mm ²)	≥ 2
Crack bridging	≥2
Water pressure	7 bar
Special mixture emulsion amount (for 25 kg powder component)	10 kg (white-coloured liquid)
Application temperature	Between +5°C and +35°C
Resistance of hardened coating	Between -25°C and +80°C

Technical data are approximately provided according to a temperature of + 20°C and a relative humidity of 50%.



Preparation of the substrate :

- The surfaces to be coated should be free of adhesive preventive foreign substances such as dust, dirt, mould oil, paint etc.; residues and wastes like cement, plaster and concrete should also be removed.
- The sub-surfaces that are not strong enough to carry themselves e.g. cracked plasters, weak surfaces, or residues of moss should be cleaned from the application surface.

Application :

- **KATRET CH FLEX UV powder component** should be poured slowly on liquid component (10 kg) that has been put into a clean container, and should be mixed by means of a mixer with low cycle until a cluster-free mixture is obtained. Mixture duration should be minimum 5 minutes. The mixture obtained at the end of the process should be rested for 3 minutes and mixed again until it becomes homogenous for 2 minutes.
- **KATRET CH FLEX UV liquid component** /the emulsion/ should be shaken well before use.
- Application should be at least two layers thick. After applying the first layer, at least 4-6 hours should be rested and second layer should be applied before waiting period exceeds 24 hours.
- The cracks that might be formed in the event of application to very wide surfaces should be prevented by means of application by leaving joints. Joints should be filled with flexible filling material.
- On the moving grounds that have cracking risk, flexible mesh for waterproofing systems can be applied as an intermediate layer between the application with the aim of forming a water isolation layer which is more flexible in order to meet the tensile stress.
- It shouldn't be applied to hot or frozen surfaces directly.

Application with machine :

KATRET CH FLEX UV is suitable for use with spray machine.

After application :

- Freshly applied surfaces should be protected against direct sun light, strong air stream, high air temperature (above +35°C), rain and frost in the initial days.
- Any kind of plaster application on the application surface or ceramic tiling works should be performed 3 days later.
- To obtain the recommended long term technical performance of the product, after the completion of the all application, the application and/or work should be covered and protected with a suitable coating or covering (plaster, screed, ceramic, tile etc...) as early as possible (depending on the product's drying time within 3 - 7 days).

Coverage :

Approximately 1,5 – 2,0 kg/m² per each 1 mm thickness.

Coverage amounts are theoretical values and it is recommended that coverage-controlled sample application is carried out before application.

Packaging :

Powder component in 25 kg craft bag, 64 sets in 1 palette. Liquid component in 10 kg plastic drum.

**Storage :**

- Dry mortar bags should be protected from water, frost and adverse weather conditions.
- They should be kept dry and cool on wooden pallets at between +10°C and +25°C in moisture free conditions.
- The torn or opened products should be closed immediately and consumed first.
- Maximum 8 bags should be stocked on each other.
- Shelf life is maximum 6 months conditional to complying with the abovementioned storage conditions.

Health and Safety Information :

For health and safety instruction, first aid measures and spillage and disposal instructions, see separate Safety Data Sheet.